

**Acid Solubility & Compressive strength of GCP Glass Fill
in comparison with competing products**

		lactic acid solubility [mm]	compressive strength [MPa]
GCP Glass Fill	1605093/1601075	-0,08	260
Ketac Fil Plus	187004	-0,10	171
Ketac Molar	181386	-0,03	242
ChemFlex	0410001927	-0,23	247
Fuji IX	0411181	-0,11	256
Ionofil Molar	401419	-0,12	191

